



Aculon Hydroxyl Functional Adhesion Promoter

Nano-Scale Adhesion-Promoting Surface Treatment

Product Information

Aculon Hydroxyl Functional Adhesion Promoter is a nano-scale surface treatment coating capable of promoting adhesion on most metal surfaces. It can be added directly to your product or applied via most traditional coating processes, including dipping, spraying, wiping, etc. It is designed to improve adhesion for coatings that cross-link with hydroxyl functional groups (e.g. urethane, melamine-formaldehyde, and phenolic-epoxy based coatings).

Solids	Solvent Soubility	Color
> 98 % Proprietary Ingredient	Soluble in Isopropanol	Off white powder

Physical Properties of Formulation (all values @ 25°C)	
Melting Point	110°C
Flash Point	N/A
Environmental	Non toxic, non-ozone depleting, flammable
Shelf Life	2 years (Unopened container)

Physical Properties of Post Treatment Coating	
Visible Light Transmission	100%
Coating Thickness	2 – 4 nm
Solvent and Chemical Resistance	High

Features

- Improved adhesion strength of paints/coatings on metal surfaces
- Excellent chemical bonding to many metal surfaces
- Does not change the appearance of the surface
- Does not leach
- Easy to apply through standard wet coating methods such as dipping or spraying.

Application Ideas

- Use to improve lead-frame adhesion in many electronics applications
- Improved bonding of an epoxy over-mold compound
- Prevent delamination of finished products
- Increase polyurethane to metal adhesion

Application Protocol

Surface Preparation/ Cleaning:

Ensure that the surface is free of any grease, fingerprints, adhesive residues or dirt (*i.e.*, water break free). This can be accomplished by first degreasing the surface with solvents or by rinsing with soap and water.

Then remove monolayer-scale contaminants. This is typically performed by using a cleaner specifically designed for the metal you are working with. Contact Aculon if you are unsure what cleaner to use and we will recommend one best suited for your application. The substrate should be water break-free before continuing to coating steps.

Treatment Application:

Adding the powder:

Test in your product by adding from 0.1% up to 5% by weight of this powder.

Test the powder in solvents of your choice and add at the levels stated above, then apply as follows:

Spray: Spray the solution onto the substrate using double passes. Post-application curing is recommended for best performance. **Spray Equipment Suggestions;** HVLP (Binks Mach 1), HVLP (Devilbiss JGHV), Air Atomization (Devilbiss MBC gun) and Airless (Graco Model 225-292 President Pump Series A).

Dip: Immerse the substrate in the solution for five minutes. If a shorter dip time is necessary, then a post-cure is recommended for optimal performance (sonication while dipping can boost performance in some cases).

Dip Coating with Sonication: Ensure the substrate is clean. Completely submerge the substrate in the solution and sonicate for five minutes. Remove substrate from the solution and allow to air dry, preferably in a clean area.

Drying/ Curing: If curing is necessary (short dip times or spray-application), the treated substrates are best cured at 120°C peak metal temperature for approximately 30 seconds. For silicon and titanium oxides, lengthening the cure time to 5 minutes is recommended.

Note: If being used to adhere a high viscosity or low-reactive resin system, especially if such coating is not cured after application, then it is suggested to do a post cure rinsing step (or post-treatment rinse if curing was not performed) for best performance. Furthermore, if a UV-curable coating system is being used, then it may be necessary to modify the curing parameters to ensure sufficient radical generation near the surface of the monolayer to achieve optimal adhesion.

Equipment Cleaning: Clean all equipment with alcohol (e.g., Isopropanol) or the solvent used.

Safety, Handling, Storage, Shelf Life:

Store in a cool (~25°C) and dry area, and keep away from direct sunlight. See this product's MSDS for proper handling and fire hazard data. When stored properly, product has a 2 year shelf life.

For Additional Information:

To request additional product information or sales assistance, contact Aculon's Technical Team, at 858-350-9474. For information on other Aculon products, please visit our website at www.aculon.com.

Product Use: All statements, technical information and recommendations contained in this document are based on tests or experience that Aculon believes to be dependable. However, many factors beyond Aculon's control can affect the use and effectiveness of an Aculon product in a particular use or application, including conditions under which the product is used and the time and conditions in which the product is expected to perform. Since these factors are exclusively within the user's knowledge and control, it is essential that the user evaluate the Aculon product to determine whether it is fit for a specific purpose and suitable for the user's method of application.

Warranty and Liability: Aculon makes no warranty or representation, expressed or implied, by operation of law or otherwise, as to the merchantability or fitness for a particular purpose of the goods arising out of a course of dealing, custom or usage of trade. Aculon shall not be liable for any defect in the goods sold hereunder and customer releases Aculon from any and all liability for negligence. Aculon will not be liable for consequential, incidental or any damages other than repair or replacement of defective good or refund of the purchase price paid for such defective goods.

Aculon • 11839 Sorrento Valley Road • San Diego • California • 92121
• Tel: +1 858-350-9474 • Email: info@aculon.com



